

TECORELEASE Silicure

Charakteristik:	TECORELEASE Silicure are technical release papers made of one-side coated, machine smooth, white wood-free paper. The release coating is done with the non polluting, solvent-free electron beam curing technology (EBC). The result is a surface that releases easily from a multitude of substances, especially duro-plastics resins based on melamine, urea and phenol formaldehyde.
Basepaper weight	70 - 180 g/sqm ± 6%
Width	up to 2180 mm
Roll length	as per agreement
Temperature resistance	Temporarily up to 180°C
Release Coating	Solvent-free coating based on radiation curable polymers and additives to optimize release properties and to adjust gloss level.
Ecological Details	TECORELEASE Silicure release papers are free of toxic heavy metals. The release coatings are free of hardener. TECORELEASE Silicure release papers are technically free of chromium and chlorine.
Storage	6 months cool and dry in original packaging (approx. 20°C, 55-65% air humidity)
Disposal	TECORELEASE Silicure release papers, if not to be reused, may easily be disposed via a domestic refuse dump or an incinerator. The deposit has to be made in accordance with responsible authorities.

The information provided in this specification is based on actual practice and on the results of in-house testing, and is consistent with the current level of our knowledge. This information is intended merely as a guide and shall not be deemed to provide any warranty of specific product properties or suitability for a specific application. Since we have no influence on materials and processing conditions, we cannot be held liable for anything arising from this specification. This specification has a validity of 12 months after date of issue.

Our international terms and conditions of sale and delivery apply in all instances. Valid versions of terms and conditions can be found on our website www.surteco.com and can also be sent upon request. Your adverse or deviant business terms do not place any obligation upon us.

Contact:

SURTECO GmbH • Robert-Linnemann-Str. 21-27 • 48336 Sassenberg • Deutschland • T: +49 2583 29-0 • info@surteco.com • www.surteco.com

Head Office:

SURTECO GmbH • Am Brühl 6 • 86647 Buttenwiesen • Deutschland • T: +49 8274 51-0 • F: +49 8274-512 • info@surteco.com • www.surteco.com